

### GENERAL DESCRIPTION

#### Definition

Matt waterbased interior paint for walls and ceilings producing a particularly high-quality finish, highly suitable for retouching.

#### Composition

Waterbased alkyd resin binder.

#### Properties

- «absolutely matt» finish
- film has extended wet edge time
- finish is free of brush or roller marks, even in low-angled light and over large surface areas
- highly suitable for retouching
- direct bonding on absorbent surfaces (prior application of a base coat is not, as a general rule, necessary)
- two coats can be applied directly on plasterboard
- very good wet abrasion resistance

#### Area of application

*Classidur HydroFinish* is highly suitable for creating particularly high-quality finishes. Outstanding features are the total absence of brush or roller marks, even in low-angled light and over large surface areas, suitability for retouching, deep matt finish and excellent smoothness. In addition, its good resistance to wet abrasion makes *Classidur HydroFinish Mat* perfectly suited to application on walls.

### CHARACTERISTICS ON DELIVERY

Viscosity:	viscous
Colour:	white
Odour:	negligible
Shelf life (20°C):	at least 12 months in tightly closed containers. Protect from heat and frost.
Packaging:	5l – 12,5l
VOC:	2004/42/CE A/a 30 g/l (2010) max. 30 g/l

### RESULTS OF MEASUREMENTS

Appearance:	totally matt (< 1,2% at angle of 85°)
Density:	1.56 (average)
Extrait sec:	64 % by weight (average)

#### Drying time (20°C and H.R. <65%):

- touch-dry after about 1 hour;
- ready for a second coat after about 4 hours;
- Totally dry and hard overnight (48 hours);
- The resistance to wet abrasion and polishing is reached after minimum 5 days of hardening.

A low temperature and high humidity level will slow down drying process.

Covering power : class 2 EN 13.300 for 8 m<sup>2</sup>/l

Wet scrub resistance : class 1 EN 13.300

### APPLICATION

#### State of substrate

dry, dust-free and coherent

#### Method of application

brush, roller

Please contact our technical service for an airless application.

#### Dilution

- On normal absorbent substrates : ready for use. Dilute 1st coat with max. 3% water.
- On very absorbent substrates (based smoothing plaster, plaster blocks...) : dilute 1st coat with about 10% water.

#### Cleaning of tools

With water immediately after application.

#### Tinting

With *ClassiMix* up to 5% or universal tinting pastes up to 3%.

#### Minimum application temperature

+8°C (support temperature)

#### Consumption

8-11 m<sup>2</sup>/l according to the nature and absorption of the substrate.

#### Application system

1-2 coats depending substrate. In case of dirty substrates, use prior to the application an undercoat and apply:

- 1 x *Classidur Universal Primer Xtrem*
- 1 x *Classidur HydroFinish Mat*

#### Remarques

- apply preferably with polyamide textured roller, 12-14 mm,
- It is advised not to use *Classidur HydroFinish Mat* in humid premises,
- *Classidur HydroFinish Mat* is comprised of alkyd resins - not to be used on fresh concrete or other alkaline bases (risk of saponification),
- do not apply on distempere substrates; prefer *Classidur Goldenclassic* for this application,
- *Classidur HydroFinish Mat* is not a primer to be covered,
- Remove foodstuffs before applying and during drying,
- Use only in well-ventilated areas,
- Do not empty into drains,
- Supply in accordance with the local regulations of the disposal and/or the recycling. Incorrectly emptied bundles are special refuse,
- Always use clean tools.

See safety data sheet on [www.claessens.com](http://www.claessens.com)



This technical data sheet provides product information and has been compiled to the best of our knowledge. The information corresponds with the latest state-of-art technology and manufacturing experience. Having regard to the wide variety of surfaces and possible limitations with specific buildings, the purchaser / user has still the responsibility of examining the above-mentioned materials in a proper workman-like manner in respect of their suitability for the application intended under the specific conditions prevailing on site. No guarantee can accordingly be given for the basic above-mentioned examples of application and user information. Information provided is not binding and does not establish any separate rights or duties under the contract of purchase, irrespective of their being material or ancillary obligations. This publication ceases to be valid on issue of a new version. You can find the currently valid version of this technical data sheet on [www.claessens.com](http://www.claessens.com)



VERNIS CLAESSENS SA  
Avenue du Silo 6  
CH-1020 Renens  
Tel. +41 21 637 1717  
[www.claessens.com](http://www.claessens.com)